



E24065

LINEAR LOW DENSITY POLYETHYLENE EXTRUSION COATING GRADE

E 24065, is a butene comonomer based Linear Low Density Polyethylene. This grade is designed for extrusion coating applications. It offers excellent sealing properties, ESCR, tear strength and abrasion resistance in thin extrusion coatings.

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Density (23°C)	ASTM D 1505	g/cc	0.924
MFI (190°C/2.16 Kg)	ASTM D 1238	g/10 min	6.5
Ultimate Tensile Strength (MD/TD)	ASTM D882	MPa	25/20
Elongation at Break (MD/TD)	ASTM D882	%	620/745
Tensile Yield Strength (MD/TD)	ASTM D882	MPa	12/11.5
Co-efficient of Friction	ASTM D 1894	-	
Static			0.79
Dynamic			0.69

*Typical Characteristics and not to be taken as specifications

** Typical Values (Mechanical) with 40 μ film made with 1.8 mm die gap & 2.25 BUR

Applications

Coating on woven fabrics, paper aluminium foil.

Regulatory Information

- Meets the requirements stipulated in standard IS : 10146-1982 on "Specification for Polyethylene for safe use in contact with foodstuffs, pharmaceuticals, and drinking water". It also conforms to the positive list of constituents as prescribed in IS : 10141-1982. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21, 177.1520, Olefin polymers.

Storage Recommendations

- Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited, Polymer Research and Technology Centre,
Swastik Mill Compound, V.N. Purav Marg, Chembur, Mumbai-400 071. Tel.: +91-22-6767 7000. E-mail: polymer_patsupport@ril.com Website: www.ril.com

• The information and data presented herein is true and accurate to the best of our knowledge. No warranty or guarantee expressed or implied, is made regarding performance or otherwise. This information and data may not be considered as a suggestion to use our products without taking into account existing patents, or legal provisions or regulations, whether national or international. • The user of any information and/or data is advised to obtain the latest details from any of the offices of the company or its authorised agents, as the information and/or data is subject to change based on the research and development work undertaken by the company.

Updated as of May, 2007