



MARPOL
LDF 700-B
Low Density Polyethylene



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index	.25	D 1238
Density	0.920	D 792
Dart Drop Impact F50 (grams)	140	D 1709
Tensile Strength (psi)	MD 4200 TD 2900	D 882
Elongation (%)	MD 105 TD 400	D 882
1% Secant Modulus (psi)	MD 27000 TD 32000	D 882
Haze (%)	30	D 1003

Additives: Medium Antiblock (3000 PPM)

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.