

Low Density Polyethylene Aramco LDPE E1970

Product Description

Aramco LDPE E1970 is a low density polyethylene resin which has good bonding strength with various substrates, low neck-in properties and excellent process ability for thinner coating. Aramco LDPE E1970 is not formulated with any additive.

Typical Applications

Extrusion coating on polyester film, paper, aluminum foil and BOPP film.

Physical properties	Unit	Test Method	Value ⁽¹⁾
Melt Flow Rate (190°C/2.16kg)	g/10min	ASTM D1238	7.0
Density	kg/m³	ASTM D792	919
Mechanical Properties ⁽²⁾			
Tensile Strength at Break ⁽³⁾	MPa	Petro Rabigh Method	14
Tensile Elongation at Break ⁽³⁾	%	Petro Rabigh Method	550
Stiffness	МРа	ASTM D747	165
ESCR	h	ASTM D1693	1.9
Thermal Properties			
Vicat Softening Point ⁽²⁾	°C	ASTM D1525	86
Melting Point	°C	Petro Rabigh Method	106

⁽¹⁾ Typical values only, not to be construed as specification limits

Processing conditions: Typical processing temperature is 300 - 340 °C.

Storage and handling: Aramco LDPE E1970 should be stored in a dry and cool place with an adequate ventilation and shall be protected from UV-light at a temperature below 50 °C.

Regulations: Detailed information is provided in Safety Data Sheet and for additional specific information, please contact Saudi Aramco Products Trading Company for certificates.

Disclaimer: © Saudi Aramco Products Trading Company. All information supplied by or on behalf Saudi Aramco Products Trading Company in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Saudi Aramco Products Trading Company assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or products. Trading Company for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers and other information.

⁽²⁾ Test specimen preparation method: compression

⁽³⁾ Test speed: 200mm/min