

PRODUCT DATA SHEET



LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE LDPE

Low Density Polyethylene

LF2207M

Technical support:
Polymer Technology Services
Centre
22 Pressburg Road,
Modderfontein, 1609
South Africa

Tel: +27 (0)11 458 0700
Fax: +27 (0)11 458 0734

Sales office:
Sasol Base Chemicals
PO Box 5486
Johannesburg, 2000
South Africa

Tel: +27 (0) 10 344 5000
polymers@sasol.com

Date of issue : March 2017

www.sasol.com

Melt Index: 0.75 g/10min

Density: 0.922 g/cm³

Features

- Tubular Resin
- Good mechanical properties
- Good optical properties

Applications

- General packaging
- Shrink film
- Form fill and seal
- Boutique bags

Additives

- Antioxidant
- Medium slip
- Medium antiblock

| Typical properties (not to be construed as specifications) | | Value (SI) | Value (English) | Method |
|--|--|-------------------------|-------------------------|-------------|
| Resin Properties | Melt Index (190°C/2.16kg) | 0.75 g/10min | 0.75 g/10min | ASTM D1238 |
| | Nominal density | 0.922 g/cm ³ | 0.922 g/cm ³ | ASTM D1505 |
| Film Properties | Tensile strength at yield MD | 10 MPa | 1450 psi | ASTM D882 |
| | Tensile strength at yield TD | 10 MPa | 1450 psi | ASTM D882 |
| | Tensile strength at break MD | 22 MPa | 3190 psi | ASTM D882 |
| | Tensile strength at break TD | 20 MPa | 2900 psi | ASTM D882 |
| | Elongation MD | 440 % | 440 % | ASTM D882 |
| | Elongation TD | 580 % | 580 % | ASTM D882 |
| | Elmendorf Tear MD | 4 g/μm | 4 g/μm | ASTM D1922 |
| | Elmendorf Tear TD | 5 g/μm | 5 g/μm | ASTM D1922 |
| | Dart Drop Impact Strength (F ₅₀) | 130 g | 130 g | ASTM D1709A |
| | Haze | 7.5 % | 7.5 % | ASTM D1003 |
| | Clarity | 40 | 40 | ASTM D1746 |
| | Gloss (45°) | 60 | 60 | ASTM D2457 |
| | Coefficient of Friction (Static) | 0.1 | 0.1 | ASTM D1894 |
| | Coefficient of Friction (Dynamic) | 0.1 | 0.1 | ASTM D1894 |
| Blocking | <25 g | <25 g | ASTM D3354 | |

The above values were measured on a 50 μm film produced on a 65 mm Macchi extruder with a Macchi LDPE screw and a 250 mm die, using 208°C melt temperature, 625 mm FLH and a 2.5:1 BUR using a die gap of 0.8mm.

Blown film extrusion

MELT TEMPERATURE 190 - 210°C

| D | °C | 4 | 3 | 2 | 1 | H |
|---|-----|---|---|---|---|---|
| | 300 | | | | | |
| | 280 | | | | | |
| | 220 | | | | | |
| | 180 | | | | | |
| | 140 | | | | | |
| | 100 | | | | | |
| | 60 | | | | | |
| | 20 | | | | | |



Processing

LF2207M should be processed on a conventional LDPE extruder, but can be processed on a LLDPE extruder (wide die gap) with drawdown limitations. The optimum BUR is 2.0:1. However excellent properties are obtained at a BUR of 1.4:1 (for > 100 µm thick film). Recommended screen pack: 60/100/60 BS mesh.

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polypropylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

Regulatory & Legal Compliance

This material complies with FDA regulation 21 CFR 177.1520 when used unmodified and according to good manufacturing practices for food contact applications. Refer to applicable food contact compliance statement which is available on request.

This material is not medically approved and should therefore not be used in any such application.