

# DOW-MITSUI POLYCHEMICALS CO., LTD.

Shiodome City Center  
5-2, Higashi-Shimbashi 1-chome  
Minato-ku, Tokyo 105-7122, Japan

TEL: 81-3-6253-4006  
FAX: 81-3-6253-4262

## **Mirason™ F97219**

### **- Low Density Polyethylene Resin -**

Property	Test Method	Units	F97219B
Melt Flow Index	JIS K 7210	g/10min	0.65
Density	JIS K 7112	g/cc	0.921
Tensile strength	JIS K 7161	MPa	15
Elongation	JIS K 7161	%	550
Flexural modulus	JIS K 7106	MPa	271
Vicat soft point	JIS K 7206	°C	95
Hardness	JIS K 7215	Shore D	54
Melt point	DSC	°C	109

The data shown are typical values and should not be used for specifications.