

Linear Low Density Polyethylene

Blown Film

Product Description:

020F18A is a Linear Low Density Polyethylene manufactured using Nova Chemical's Sclairtech Solution Polymerisation Technology with following features:

- Easy processability
- Low gels
- No slip & antiblock

Recommended Applications:

LLDPE 020F18A is recommended for following applications

- Lamination films
- Cast film
- Stretch cling films
- Air bubble film

Typical Properties:

Tested Properties	Test Method	UOM	Values*
Resin Properties			
Melt Flow Index (190°C & 2.16 Kg)	ASTM D 1238	gm/10 min	2.0
Density @ 23°C	ASTM D 1505	gm/cm ³	0.918
Mechanical Properties			
Tensile Strength @ Yield (50 mm/min) MD/TD	ASTM D 882	MPa	12.5/12.0
Ultimate Tensile Strength (50 mm/min) MD/TD	ASTM D 882	MPa	33/28
Elongation at Break(50 mm/min) MD/TD	ASTM D 882	%	700/800
Dart Impact Strength (38mm dart,66cm height)	ASTM D 1709	g/μ	2.5
Tear Strength	ASTM D 1922	g/μ	3/8
Haze	ASTM D 1003	%	9

* Typical values not to be construed as specification limits. Values may change without any prior notice.

* Mechanical Properties tested on 40μ monolayer film made with 1.8 mm die gap & 2.25 BUR.

Recommended Processing Temperature: 170– 210 °C

Packaging Information:

This material is packed and available in raffia bags with net content of 25.0 Kg only. The raffia bags used conforms to the minimum strength requirements of BIS, however, customer shall take due care while handling the bag. Prolonged exposure of these bags to sunlight may deteriorate the bag's performance and cause spillage and wastage. IOCL does not warranty loss of material due to poor material handling practices.

Regulatory Information:

LLDPE 020F18A shall meet "Specification for Polyethylene for safe use in contact with Foodstuff, Pharmaceuticals and Drinking water" as per IS: 10146-1982. It also conforms to the positive list of constituents as per IS: 10141-1982. The grade and Additives incorporated shall meet with FDA: CFR Title21, 177.1520, Olefin Polymers.

Storage & Handling:

Prevent LLDPE Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the storage temperature should not exceed 50°C. Non - compliance to these precautionary measures can lead to degradation

Disclaimer: IOCL assumes no liability whatsoever in respect of application, processing or any use made of the aforementioned information or products, or any consequence thereof. No liability whatsoever shall be attached to any of the IOCL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.



Registered Office Address →
G-9, Aliyavar Jung Marg,
Bandra (East), Mumbai – 400051
Maharashtra, India.

Contact Address →
Product Application and Development Center (PADC),
Near Panipat Naphtha Cracker Complex,
Village – Bajattan, Panipat – 132140, Haryana, India

Contact Details →
Tel : +91-180-2526702, 2526704
Fax : +91-180-2528689
Web : <https://propel.indianoil.in>