

# LL7420A

## Linear Low Density Polyethylene Resin

**Special Characteristics :** InnoPlus LL7420A resin is a linear low density polyethylene with butene comonomers without slip and antiblock. This grade offers an outstanding excellent draw down in both blown and cast film processing. Films extruded from InnoPlus LL7420A have high tensile, gloss and good toughness properties. It can be used for blending with other polyethylene types, such as HDPE and LDPE.

**Typical Applications :** InnoPlus LL7420A is recommended for producing the stretch films, liners, industrial bags, refuse sacks and garbage bags.

### Typical Properties :

Properties	LL7420A	Unit	Test Method
<b><u>Physical Properties</u></b>			
Melt Index (190 °C, 2.16 kg)	2.0	g/10 min	ASTM D1238
Density	0.918	g/cm <sup>3</sup>	ASTM D792
Melting Point	121	°C	ASTM D3418
Vicat Softening Point	97	°C	ASTM D1525
<b><u>Film Properties*</u></b>			
Tensile Strength at Break (MD/TD)	31 / 23	MPa	ASTM D882
Elongation at Break (MD/TD)	600 / 800	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	195 / 220	MPa	ASTM D882
Dart Impact Strength	85	g	ASTM D1709
Tear Strength (MD/TD)	100 / 300	g	ASTM D1922
Haze	10	%	ASTM D1003
Gloss (45°)	50	-	ASTM D2457

\* film properties obtained from 25 microns film which was blown film extruded at blow up ratio 2

### Processing Condition :

The recommended temperature setting is in the range of

- 160 - 180 °C for extruder and 170 - 190 °C for die zone. (blown film)
- 210 - 270 °C for extruder and 260 - 270 °C for die zone. (cast film)

### FDA Statement :

LLDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 regulation for polyethylene used in articles that contact food except for articles used for packaging or holding food during cooking.

### Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- We assume no liability for any use of the product in combination with other materials. The information contained herein entirely relates to the product when it is not used in combination with any third party's materials.

**Note :** Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.