

LL9641U / LL9641UP

Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL9641U and LL9641UP are hexene comonomer based linear low density polyethylene designed for rotational molding applications. These are UV8 resistance level rotational molding grades which provide an excellent stiffness and a good balance between impact strength and environmental stress cracking resistance.

InnoPlus LL9641UP is a powder form of InnoPlus LL9641U.

Typical Applications : InnoPlus LL9641U and LL9641UP can be used to produce variety applications such as general molding, toys & playground equipment, outdoor storage containers, medium to large water tanks and chemical tanks.

Typical Properties :

Properties	LL9641U / LL9641UP	Unit	Test Method
<i>Physical Properties</i>			
Melt Flow Rate (190 °C, 2.16 kg)	4.0	g/10 min	ASTM D1238
Density	0.938	g/cm ³	ASTM D792
Brittleness Temperature	< -70	°C	ASTM D3418
Vicat Softening Point	118	°C	ASTM D1525
<i>Mechanical Properties (Compression specimens)*</i>			
Tensile Strength at Yield	20	MPa	ASTM D638
Tensile Strength at Break	25	MPa	ASTM D638
Elongation @ Break	950	%	ASTM D638
Flexural modulus	750	MPa	ASTM D790
Durometer Hardness	57	Shore D	ASTM D2240
ESCR, F ₅₀ (Condition A 100% Igepal)	>500	Hours	ASTM D1693

Processing Condition :

The recommended oven temperature is in the range of 260 - 290 °C.

FDA Statement :

LLDPE under the brand InnoPlus complies with U.S. FDA 21 CFR 177.1520 regulation for polyethylene used in articles that contact food except for articles used for packaging or holding food during cooking.

Disclaimer :

This Applications specified herein is for reference only and not suitable for using in the manufacturing of any products in medical and pharmaceutical sectors.

- Determination of suitability of the product for the use and purpose shall be the customer's responsibility. Customer is obligated to inspect and test the product for such suitability. Customer is responsible for appropriate, safe, legal use processing and handling of the product.
- To our best knowledge, information contained herein is true and accurate as of the date of its publication. However, we make no representations or warranties with respect to accuracy, reliability and completeness of the information contained herein for any purpose.
- No warranties, express or implied, which extend beyond the description herein are given by us. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- We assume no liability for any use of the product in combination with other materials. The information contained herein entirely relates to the product when it is not used in combination with any third party's materials.

Note : Properties reported here are typical values of the product, not to be considered as specifications.

PTT Global Chemical makes no representations as to the accuracy or completeness of the information contained herein.