

Product Data

TITANZEX HF7000 FOR FILM EXTRUSION

- CHARACTER** HF7000 is a high density polyethylene resin for tubular film extrusion. HF7000 meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 3.1a & 3.2a.
- APPLICATIONS** Very thin reinforcing film, Grocery bags, Merchandize bags, Disposal waste bags, Shopping bags
- ADVANTAGES** Excellent processability, excellent draw down capability and high film strength and rigidity

| <u>TYPICAL RESIN PROPERTIES</u> | <u>UNIT</u> | <u>TITANZEX HF7000</u> ^(a) | <u>ASTM METHOD</u> ^(b) |
|---------------------------------|-------------------|---------------------------------------|-----------------------------------|
| Melt index | g/10 min. | 0.05 | D 1238 |
| Density | g/cm ³ | 0.953 | D 1505 |

TYPICAL FILM PROPERTIES ^(c)

| Tensile Strength at Break MD/TD | kg/cm ² | 800/550 | D 882 |
|--------------------------------------|--------------------|--------------------|--------|
| Ultimate Elongation MD/TD | % | 250/660 | D 882 |
| 1% Secant Modulus MD/TD | kg/cm ² | 13000/12000 | D 882 |
| Elmendorf Tear MD/TD | g/μm | 0.3/3 | D 1922 |
| Dart Impact Strength F ₅₀ | g/μm | 11 | D 1709 |

(a) Values shown are typical and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

(c) Film properties are typical blown film of 17 microns extruded at 4:1 BUR.

Processing conditions

| | |
|-------------------|-----------------------------|
| Melt temperature | : 180 - 240°C |
| BUR | : 4:1 |
| Frost line height | : 7 - 12 times die diameter |

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

R00