



GAIL (India) Ltd.
(A Govt. of India Undertaking)
Petrochemicals Marketing Division

W50A009

High Density Polyethylene for Tape Extrusion

Application: W50A009 is recommended for manufacturing tapes of high strength (tenacity) and good elongation. Its application includes woven sacks for packaging of fertilizer, food grain, sugar, salt and other Industrial products.

It provides excellent processability and orientation characteristic with low water carry over.

Property	Values*	Unit	Test Method
Melt Flow Index (I ₂)	0.9	gm/10min	ASTM D1238
Density	0.950	gm/cc	ASTM D1505
Tensile Strength @ yield	230	kg/cm ²	ASTM D 638
Elongation @ yield	13	%	ASTM D 638
Flexural modulus	8500	kg/cm ²	ASTM D790
Vicat softening point	122	°C	ASTM D1525

* Typical characteristics of the product given purely as a guide. Mechanical properties were determined on compression molded samples.

Processing Guidelines:

Barrel temperature: 200 -260°C

Die temperature: 245 -260°C

Stretch ratio: 5.3 - 5.6

Regulatory Information:

Certificate is available on request.

Packaging & Storage:

W50A009 is available in natural colour/pellet form in 25 kg strong bags made of woven fabric. The product should be stored in dry conditions at temperature below 50°C and protected from UV light.

For any technical assistance contact:

GAIL Polymer Technology Centre

B-35/36, Sector-1, Noida, UP-201301, Tel: +91-0120-2549155/156, 2549310; Fax: 011-26185941

Website: www.gailonline.com

The information, data and suggestions contained herein are to the best of our knowledge accurate and reliable. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user specific application.

Revised in Apr'2008