

Data Sheet* Advanced-PP 1102 L

Description

Advanced-PP 1102L is a propylene homopolymer with general extrusion additivation with low water carry over. It is specifically suited for Raffia & Thermoforming Applications.

Application

Thermoformed Parts, Raffia, General Extrusion.

Regulatory Information:

The Grade Advanced-PP 1102L and additives incorporated comply with United States FDA Regulation 21CFR 177.1520 Olefin Polymers and European Regulation (EU) 10/2011 (and its amendments). Specific information is available upon request.

Properties (Typical values)

| Properties | Unit | Test method | Value |
|---|---------------------|---------------|-------|
| Melt Flow Rate | | | |
| Melt flow rate (230°C / 2.16 KG) | g / 10 min | ISO 1133 | 5.0 |
| Mechanical Properties | | | |
| Tensile modulus of elasticity (v= 1 mm/min) | MPa | ISO 527-2 | 1500 |
| Tensile stress at yield (v= 50 mm/min) | MPa | ISO 527-2 | 34 |
| Tensile strain at yield (v= 50 mm/min) | % | ISO 527-2 | 9 |
| Tensile strain at break (v= 50 mm/min) | % | ISO 527-2 | >50 |
| Charpy impact strength unnotched (+23°C) | kJ/m ² | ISO 179/1eU | 140 |
| Charpy impact strength notched (+23°C) | kJ/m ² | ISO 179/1eA | 3.5 |
| Izod Impact strength Notched (+23°C) | kJ/m ² | ISO - 180 /1A | 3.5 |
| Ball indentation hardness (H 358/30) | MPa | ISO 2039-1 | 74 |
| Thermal Properties | | | |
| Melting point, DSC | °C | ISO 3146 | 163 |
| Heat deflection temperature ----- HDT/B (0.45 Mpa) | °C | ISO 75-2 | 85 |
| Vicat softening temperature ----- VST/A50 (10 N) | °C | ISO 306 | 154 |
| Other Properties | | | |
| Density | g / cm ³ | ISO 1183 | 0.91 |

* Provisional

Values given here are typical and should not be interpreted as specification. In a view of many factors that may affects processing and application, these data do not relieve the receiver to this information from the responsibility of carry out their own test and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for specific purpose of the product made with or on the basis of the information in this publication.

Mar14

Advanced Petrochemical Company
Saudi Joint Stok Company

Headquarters - Dammam P.O. Box 7215 Dammam 31462 Saudi Arabia
Tel: +966 3 809860 Fax: +966 3 8098750 C.R. 2050049604

Manufacturing Plant Site - Jubail P.O. Box 11022 Jubail 31961 Saudi Arabia
Tel: +966 3 3591000 Fax: +966 3 356065 C.R. 2055008094
Paid up capital: S.R. 1,639,950,000,00

الشركة المتقدمة للبتروكيماويات
شركة مساهمة سعودية

المركز الرئيسي - الدمام ص.ب. ٧٢١٥ - الدمام ٣١٤٦٢ المملكة العربية السعودية
صانف: +٩٦٦٣٨٠٨٨٧٠ فاكس: +٩٦٦٣٨٠٩٨٧٠ س.ت. +٩٦٦٣٨٠٤٩٦٠

إدارة المصنع - المينل ص.ب. ١١٠٢٢ - المينل ٣١٩٦١ المملكة العربية السعودية
صانف: +٩٦٦٣٥٩١٠٠٠ فاكس: +٩٦٦٣٥٩١٠٦٠ س.ت. +٩٦٦٣٥٩٠٠٠٤٠
رأس المال المدفوع: ١,٦٣٩,٩٥٠,٠٠٠,٠٠٠

www.advancedpetrochem.com