



TECHNICAL DATA SHEET

Product Name

SCG™ PP

Product Type

Homopolymer Polypropylene for Water Quenched

Product Grade

P601F

Product Description

P601F is a homopolymer polypropylene resin for water-quenched blown film resin. This grade is contain high slip and antiblock agent and recommended for applications that film thickness is lower than 50 um.

Typical Application

- Food packaging
- Outer packing bag
- Shopping bag

Product Characteristics

- High productivity
- Good optical properties
- Excellent open-ability
- Food contact applicable
- High Slip and Anti-block content

International

- U.S FDA 21 CFR 177.1520
- Regulation (EU) No.10/2011
- Packaging and Packaging waste Directive 94/62/EC/CONEG

Physical Properties

Property	Test Method	Value	Unit
Melt Flow Rate	ASTM D 1238 @ 230 °C, 2.16 kg	10	g/10 min
Density	ASTM D 1505	0.910	g/cm ³
Melting Point	ASTM D 2117	160	°C
Film Properties			
Tensile Strength at Break	ASTM D 882	MD: 300*, TD: 100*	kg/cm ²
Tensile Modulus, 2% Secant	ASTM D 882	MD: 5000*, TD: 4800*	kg/cm ²
Elongation at Break	ASTM D 882	MD: 500*, TD: 100*	%
Haze	ASTM D 1003	3*	%

Note: (*) Properties obtained from film produced on a pilot line at TPE, 35 micron, cooling water temperature 25 °C, MD = Machine Direction, TD = Transverse Direction. Conversion factor for changing unit from kg/cm² to MPa is divided by 10.2



TECHNICAL DATA SHEET

Product Name

SCG™ PP

Product Type

Homopolymer Polypropylene for Water Quenched

Product Grade

P601F

Processing Guidelines

The actual extrusion condition depends on type of using machine, size and film thickness of product required. Generally, melt temperature should be 190-210 °C, BUR = 1.5:1 is recommended, cooling water temperature not over than 20 °C.

Product Technical Assistance

For technical assistance or further information on this product or any other SCG Chemicals' products, please contact your SCG Chemicals technical service at the address or telephone number as specified below.

Product Available Form

- Pellet

Product Packaging

- 25 kg loose bag
- 25 kg stretch wrap palletized
- 750 kg big bag
- Seabulk container

Storage

- Store in original container in tidy according to the manual of Handling and Storage from Thai Polyethylene Company Limited/Thai Polypropylene Company Limited.
- Product(s) should be stored in dry and dust free location at temperature below 50 °C and protected from direct sunlight and/or heat, well-ventilated area, away from incompatible materials and food and drink, as this may lead to quality deterioration, which results in odor generation and colour changes and can have negative effects on the physical properties of this product.
- Keep container tightly closed and sealed until ready for use. Containers that have been opened must be carefully resealed and kept upright to prevent leakage. Do not store in unlabelled containers. Use appropriate containment to avoid environmental contamination.
- The storage area should be stable and not be slopped.

Safety

- The product is not classified as a hazardous material.
- Please see our Material Safety Data Sheet for details on various aspects of safety, recovery, and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.

Recycling

- The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.
- Please see our Material Safety Datasheet for details on various aspects of safety, recovery and disposal of the products; for more information, contact your SCG Plastics/SCG Performance Chemicals technical service.



TECHNICAL DATA SHEET

Product Name

SCG™ PP

Product Type

Homopolymer Polypropylene for Water Quenched

Product Grade

P601F

Related Document

- The latest version of this document will be available at our website, www.scgchemicals.com, or can be obtained from the SCG Plastics/SCG Performance Chemicals technical service.
- The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product
 - Material Safety Datasheet
 - Statement on compliance to food contact regulations

Disclaimer

- The Applications specified herein is for reference only.
- It is customer's responsibilities to inspect and test the product for suitability of the customer's own use and purpose. The customer is responsible for appropriate, safe, legal use, processing and handling of the product.
- To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication. We however do not assume any liability whatsoever for the accuracy and completeness of the information contained herein.
- We make no warranties which extend beyond the description herein. Nothing herein shall constitute any implied warranty of merchantability or fitness for a particular purpose.
- No liability can be accepted in respect of the use of the product in conjunction with other materials. The information contained herein relates exclusively to the product when it is not used in conjunction with any third party's materials.