



## XUS 89770.05 Experimental Linear Low Density Polyethylene

### Description

XUS 89770.05 Experimental Linear Low Density Polyethylene is a high-performance polyethylene house abuse resin for a wide variety of blown film applications requiring excellent dart, puncture, and optics. Applications include protein, pet food, frozen food, fresh produce, cheese, industrial films, heavy duty shipping sacks, shrink, construction, and agricultural.

### Main Characteristics

- Excellent toughness properties.
- Excellent optical properties.
- Good sealing performance.

### Complies with

- U.S. FDA FCN 1539
- Europe Commission Regulation (EU) No 10/2011

Consult the regulations for complete details.

### Additive

- Antiblock: 5500 ppm
- Slip: 990 ppm
- Processing Aid: Yes

### Properties<sup>1</sup>

Physical	Nominal Value	Unit (English)	Test Method <sup>2</sup>
Density	0.921	g/cm <sup>3</sup>	ASTM D792
Melt Index (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Melting Temperature (DSC)	233	°F	Internal Method
<b>Films</b>			
Film Thickness-Tested	2	mil	Internal Method
Film Puncture Energy	25	in·lb	Internal Method
Film Puncture Force	12	lbf	Internal Method
Film Toughness			ASTM D882
MD	1420	ft·lb/in <sup>3</sup>	
TD	1355	ft·lb/in <sup>3</sup>	
Secant Modulus			ASTM D882
1% Secant, MD	31100	psi	
2% Secant, MD	26900	psi	
1% Secant, TD	30500	psi	
2% Secant, TD	26600	psi	

1. Typical properties: these are not to be construed as specifications. Users should confirm results by their own tests.
2. ASTM: American Society for Testing and Materials.

## Properties (Cont.)

Films	Nominal Value	Unit (English)	Test Method
Tensile Strength			ASTM D882
MD: Yield	1420	psi	
TD: Yield	1400	psi	
MD: Break	7750	psi	
TD: Break	7250	psi	
Tensile Elongation			ASTM D882
MD: Break	600	%	
TD: Break	600	%	
Dart Drop Impact	1450	g	ASTM D1709A
Elmendorf Tear Strength			ASTM D1922
MD	660	g	
TD	710	g	
<b>Optical</b>			
Haze	17	%	ASTM D1003
Gloss (45°)	56	%	ASTM D2457

### Additional Information

Fabrication Conditions for Blown Film:

- Screw Size: 3.5 in.
- Screw Type: DSB II
- Die Gap: 70 mil (1.8 mm)
- Melt Temperature: 450°F
- Output: 9.9 lb/hr/in. of die circumference
- Die Diameter: 8 in.
- Blow-Up Ratio: 2.5:1
- Screw Speed: 35 rpm
- Frost Line Height: 35 in.

## Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

## Medical Applications Policy

Any and all medical application use of Dow materials, whether a device, a component, or any type of primary or secondary packaging of a medically related object or substance, needs to be reviewed and approved by Dow before any Dow material can be tested in such application.

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

For further information contact your Dow sales or technical representative to request a Medical Application Review Request Form.

Additional details of Dow's Medical Applications Policy are available at:  
<https://www.dow.com/en-us/support/product-safety.html>

## Tobacco and Marijuana Policy

Dow does not support or intend for its products to be used, directly or indirectly, in the production of tobacco, the manufacture of tobacco products, the manufacture and use of electronic cigarettes (including vaping devices), the production of marijuana, or the manufacture of marijuana products intended for human consumption, where the Dow product (or its residues) may be present in the finished product or be alleged to facilitate the delivery of nicotine, other tobacco components, marijuana, or marijuana components.

## Harmful Applications Policy

Dow does not intend for its products to be used in applications specifically intended to harm humans.

Contact:  
[www.dow.com/contact](http://www.dow.com/contact)

NOTICE: No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, the Customer is responsible for determining whether products and the information in this document are appropriate for the Customer's use and for ensuring that the Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Dow assumes no obligation or liability for the information in this document. **NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.**

NOTICE: If products are described as "experimental" or "developmental": (1) product specifications may not be fully determined; (2) analysis of hazards and caution in handling and use are required; (3) there is greater potential for Dow to change specifications and/or discontinue production; and (4) although Dow may from time to time provide samples of such products, Dow is not obligated to supply or otherwise commercialize such products for any use or application whatsoever.

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

For additional information, not covered by the content of this document, contact us via our web site  
[http://www.dow.com/products\\_services/](http://www.dow.com/products_services/).

This document is intended for use within Asia Pacific, Europe, North America.

