

**DOW-MITSUI POLYCHEMICALS CO., LTD.**

***EVAFLEX™ EV210ETR***

Property	Test Method	Units	EV210ETR
VA Content	JIS K7192	wt%	28
MFR	JIS K7210	g/10min	400
Density	JIS K7112	Kg/m <sup>3</sup>	950
Tensile Strength	JIS K7161	MPa	5
Elongation	JIS K7161	%	900
Stiffness	JIS K7106	MPa	13
Hardness(Shore A)	JIS K7215	Degree	81
Vicat Softening Point	JIS K7206	°C	<34
Melting Point	JIS K7121	°C	73

The data shown are typical values and should not be used for specifications.