



Technical Data Sheet

INNATE™ TH61 Precision Packaging Resin

Description

INNATE™ TH61 Precision Packaging Resin is designed for exceptional toughness in combination with sealing performance while also delivering robust processability. It has exceptional low-temperature toughness and flex-crack resistance, making it a versatile resin that can meet the needs of demanding end-use applications.

Complies with

- U.S. FDA FCN 424
- EU, No 10/2011

Consult the regulations for complete details.

Properties¹

Physical	Nominal Value	Unit	Test Method ²
Density	0.912	g/cm ³	ASTM D792
Base Density ³	0.914	g/cm ³	Internal Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.85	g/10 min	ASTM D1238
Films			
Film Thickness - Tested	51	µm	
Film Puncture Energy	10.5	J	Internal Method
Film Puncture Force	106	N	Internal Method
Film Puncture Resistance	26.3	J/cm ³	Internal Method
Secant Modulus			ASTM D882
2% Secant, MD	145	MPa	
2% Secant, TD	169	MPa	
Tensile Strength			ASTM D882
MD: Yield	8.32	MPa	
TD: Yield	8.51	MPa	
MD: Break	51.2	MPa	
TD: Break	51.9	MPa	
Tensile Elongation			ASTM D882
MD: Break	580	%	
TD: Break	660	%	

1. Typical properties: these are not to be construed as specifications.
2. ASTM: American Society for Testing and Materials
3. Base Density is estimated using the assumption that every 1000 ppm of antiblock in the finished product raises the density of the polymer by 0.0006 g/cm³. Base Density is the estimated density of the polymer if it did not contain any antiblock.

Properties (Cont.)

Films	Nominal Value	Unit	Test Method
Dart Drop Impact ⁴	2100	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	520	g	
TD	820	g	
Thermal			
Vicat Softening Temperature	98.0	°C	ASTM D1525
Melting Temperature (DSC)	123	°C	Internal Method
Optical			
Gloss (45°)	51		ASTM D2457
Haze	14.0	%	ASTM D1003

Extrusion Notes

Fabrication Conditions for 2 mil monolayer Blown Film:

- Die Diameter: 8 in.
- Screw Type: DSB II
- Die Gap: 90 mil
- Melt Temperature: 433°F
- Output: 10.3 mlb/hr/in. of die circumference
- Screw Size: 3.5 in.
- Blow-Up Ratio: 2.5 to 1
- Screw Speed: 35 rpm
- Frost Line Height: 40 in.

4. Method A.

Product Stewardship

The Dow Chemical Company and its subsidiaries ("Dow") has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our Product Stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our Product Stewardship program rests with each and every individual involved with Dow products — from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

Medical Applications Policy

Any and all medical application use of Dow materials, whether a device, a component, or any type of primary or secondary packaging of a medically related object or substance, needs to be reviewed and approved by Dow before any Dow material can be tested in such application.

Medical Applications Policy (Cont.)

Dow requests that customers considering use of Dow products in medical applications notify Dow so that appropriate assessments may be conducted. Dow does not endorse or claim suitability of its products for specific medical applications. It is the responsibility of the medical device or pharmaceutical manufacturer to determine that the Dow product is safe, lawful, and technically suitable for the intended use. **DOW MAKES NO WARRANTIES, EXPRESS OR IMPLIED, CONCERNING THE SUITABILITY OF ANY DOW PRODUCT FOR USE IN MEDICAL APPLICATIONS.**

For further information contact your Dow sales or technical representative to request a Medical Application Review Request Form.

Additional details of Dow's Medical Applications Policy are available at:
<https://www.dow.com/en-us/support/product-safety.html>

Tobacco and Marijuana Policy

Dow does not support or intend for its products to be used, directly or indirectly, in the production of tobacco, the manufacture of tobacco products, the manufacture and use of electronic cigarettes (including vaping devices), the production of marijuana, or the manufacture of marijuana products intended for human consumption, where the Dow product (or its residues) may be present in the finished product or be alleged to facilitate the delivery of nicotine, other tobacco components, marijuana, or marijuana components.

Harmful Applications Policy

Dow does not intend for its products to be used in applications specifically intended to harm humans.

Contact:
www.dow.com/contact

NOTICE: This data is based on information Dow believes to be reliable, as demonstrated in controlled laboratory testing. They are offered in good faith, but without guarantee, as conditions and method of use of Dow products are beyond Dow's control. Dow recommends that the prospective user determine the suitability of these materials and suggestions before adopting them on a commercial scale.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability for the accuracy and completeness of such information.

This document is intended for use within Europe, Middle East and Africa.

